

MICAM's E7 Grade is an epoxide resin laminate, based on a medium weave glasscloth, with excellent electrical, mechanical and thermal characteristics, when compared to conventional laminates.

Characteristics	Excellent electrical and mechanical properties High Temperature rating
Colours	Translucent Green/Yellow
Thickness	0.5 mm to 100 mm available on request
Sheet Size	1220 mm x 920 mm (panel sizes cut on request)

	units	test method
GENERAL PROPERTIES		
Relative Density	1.8 -	IEC 1183-A
Thermal Index class F	155 °C	IEC 216
Water Absorption	10 mg/50x50x3 mm	IEC 62-1
MECHANICAL PROPERTIES		
Flexural Strength (X axis)	500 MPa	ISO 178
Flexural Strength (Y axis)	420 MPa	ISO 178
Flexural Modulus (X axis)	18,000 MPa	ISO 178
Flexural Modulus (Y axis)	14,000 MPa	ISO 178
Flexural Modulus (Z axis)	10,000 MPa	ISO 178
Flexural Strength at Elevated Temp ^{#1}	300 MPa	ISO 178
Izod Impact Strength	70 kJ/m ²	ISO 180/2A
Shear Strength, parallel	57 MPa	EN 60893-2
Tensile Strength (X axis)	345 MPa	ISO 527
Tensile Strength (Y axis)	300 MPa	ISO 527
Compressive Strength Flatwise	545 MPa	ISO 604
ELECTRICAL PROPERTIES		
Insulation Resistance after immersion in water	5 x 10 ⁵ MΩ	IEC 167
Dielectric Strength Flatwise (in oil at 90°C)	18 MV/m (1.6 mm)	IEC 243-1
Dielectric Strength Edgewise (in oil at 90°C)	65 kV (3 mm)	IEC 243-1
Dissipation Factor at 50 Hz	0.008 -	IEC 250
Dissipation Factor at 1 MHz	0.01 -	IEC 250
Permittivity at 50 Hz	4.7 -	IEC 250
Permittivity at 1 MHz	4.7 -	IEC 250
Comparative Tracking Index	200 V	IEC 112

#1: 1 hr/150°C and tested at 150°C #2: Tested after stoving – 160/4, 20/8

SPECIFICATION COMPLIANCE

EN 60893-3-2:EPGC203; NEMA LI-1 G-11; BS 3953:EP5+7

ENVIRONMENTAL COMPLIANCE

RoHS compliant; REACH compliant

QUALITY SYSTEM APPROVAL

Certified by NSAI to I.S. EN ISO9001:2015

MICAM LIMITED · TEL + 353 22 21345 · EMAIL info@micam.com · WEB www.micam.com

